

Endura Manufacturing Co. Ltd 12425 - 149 Street NW Edmonton, Alberta, Canada T5L 2J6 Phone: +1-780-451-4242/ 1-800-661-9930 www.endurapaint.com

## **FA777 Flattening Agent**

## **Technical Data Sheet (TDS)**

### **Product Description**

**FA777 Flattening Agent** is a highly concentrated, liquid flattening agent for use in reducing the gloss levels of Endura polyurethane topcoats. The gloss level can be varied from Medium Gloss to No Gloss.

#### Product features:

- Reduced reflectance
- Easy to measure and mix
- Does not significantly affect viscosity
- Allows for custom gloss reduction
- Does not water spot after 18 hour cure

#### Recommended Uses

FA777 Flattening Agent is suitable for use in the following Endura Topcoats.

- EX-2C Topcoat
- EX-2C Low VOC Topcoat
- EX-2C C.C. Topcoat
- EX-2C T2FK Topcoat
- EX-2C T2FK Low VOC Topcoat
- EX-2C Clear 100
- EX-2C Clear 221
- EX-2C Midcoat Clear 100
- Clarity Clear
- Excel D2M & D2M HS
- G90 Low VOC Topcoat
- UltraFlex Topcoat
- UltraFlex Low VOC Topcoat
- Kappa Clear Fast & Slow
- Polyglass Edge

FA777 Flattening Agent is not intended for use with any other products.

### **Product Characteristics**

Specific Gravity: (77°F (25°C) and 50% RH)	0.945			
Shelf Life:				
FA777 Flattening Agent	1 years			
For unopened product (77°F (25°C))				

## **Mixing Ratio**

#### **Endura Gloss Standards:**

	Gloss	At 60 Degrees
Level 1	No Gloss	0-5
Level 2	Lo Gloss	10-20
Level 3	Med Gloss	40-50

The following mixing ratio table applies to all the Endura polyurethane topcoats listed and should only act as a guide:

The amount of pigment in a formula will affect the gloss and will require a different mix ratio of the FA777 to achieve the different gloss levels.

## The mixing chart below should be used as a guide to achieve the desired gloss.

Volume ratio with EX-2C Part A : Part B: FA777	Clear 100 FUA0100 No Pigment	Black 160 FUA 0160 Low Pigment	White 120 FUA0120 High Pigment
100 : 100: 60	N/A	N/A	Med Gloss
100 : 100: 70	Med Gloss	Med Gloss	N/A
100 : 100: 75	N/A	N/A	Low Gloss
100 : 100: 80	Low Gloss	Low Gloss	N/A
100 : 100: 90	No Gloss	No Gloss	No Gloss
100 : 100: 100	No Gloss	N/A	N/A

FA777 must be added after A&B components have been mixed.

Addition of FA777 will cause clear topcoats to turn somewhat opaque.



Endura Manufacturing Co. Ltd 12425 - 149 Street NW Edmonton, Alberta, Canada T5L 2J6 Phone: +1-780-451-4242/ 1-800-661-9930 www.endurapaint.com

# **FA777 Flattening Agent**

**Technical Data Sheet (TDS)** 

FA777 must be mixed in the same proportions for each batch. Inconsistent measuring will result in gloss variation between batches. Mixing ratio depends upon topcoat used.

## **Dry Times**

The use of FA777 will not affect the topcoat re-coat window.

Note: The recoat window is subject to ambient conditions (temperature and humidity) and good airflow and film build of the topcoat.

## Ordering Information (sizing)

Available in Pints, Quarts and Gallons Other custom sizes may be available.

Pint (473 ml)	
FA777	FAD0002-010
Quart (946 ml)	
FA777	FAD0002-020
Gallon (3.78 L)	
FA777	FAD0002-030

## **Safety Precautions**

Please refer to all Safety Data Sheets (SDS) before using this product. SDS sheets can be found on our website at www.endurapaint.com.